

ABSTRACT OF THE DISCLOSURE

The present invention intends to provide a manufacturing method for a plasma display panel, so as to overcome problems associated with a withstanding voltage of a dielectric glass layer.

As can be seen from Fig. 6 (c), glass particles have angular shapes after grinding with a grinder, but as the surface of them has been melted, they are converted into spheroids. Those glass particles can get wet evenly, so that a binder 64 evenly adheres to the surface of a glass particle 63 when a glass paste including the glass particles is applied to the surface of a substrate. In this case, there is a scarce possibility for a gas, generated by baking the binder, to remain in the form of bubbles in a formed dielectric glass layer. As shown in Fig. 6(d), there are fewer bubbles AH remaining in a completed dielectric glass layer than in a dielectric glass layer of Fig. 6(b).



(43) 国際公開日
2001 年 6 月 14 日 (14.06.2001)


PCT

(10) 国際公開番号
WO 01/43158 A1

- | | | |
|-----------------------------|---|---|
| (51) 国際特許分類: | H01J 9/02, 11/02 | (WATANABE, Taku) [JP/JP]; 〒576-0034 大阪府交野市天野が原町4-28 303 Osaka (JP). 青木正樹 (AOKI, Masaki) [JP/JP]; 〒562-0024 大阪府箕面市粟生新家5-12-1 Osaka (JP). 鈴木茂夫 (SUZUKI, Shigeo) [JP/JP]; 〒573-0093 大阪府枚方市東中振2-9-1-315 Osaka (JP). |
| (21) 国際出願番号: | PCT/JP00/08659 | |
| (22) 国際出願日: | 2000 年12 月7 日 (07.12.2000) | |
| (25) 国際出願の言語: | 日本語 | (74) 代理人: 中島司朗 (NAKAJIMA, Shiro); 〒531-0072 大阪府大阪市北区豊崎三丁目2番1号 淀川5番館6F Osaka (JP). |
| (26) 国際公開の言語: | 日本語 | |
| (30) 優先権データ: | | (81) 指定国 (国内): CN, KR, US. |
| | 特願平11/348931 1999 年12 月8 日 (08.12.1999) JP | |
| (71) 出願人 (米国を除く全ての指定国について): | 松下電器産業株式会社 (MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD.) [JP/JP]; 〒571-8501 大阪府門真市大字門真1006番地 Osaka (JP). | 添付公開書類:
— 国際調査報告書 |
| (72) 発明者; および | | 2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。 |
| (75) 発明者/出願人 (米国についてのみ): | 渡邊 拓 | |

(54) Title: PLASMA DISPLAY PANEL PRODUCTION METHOD

(54) 発明の名称: プラズマディスプレイパネルの製造方法



(S7) Abstract: A plasma display panel production method for combating a problem with the withstand voltage of a dielectric glass layer. Surface-fusion-treated glass particles (63) are almost in a spherical shape because the squarish portions of glass particles (61) just after crushed by a crusher have been smoothed out. Since such surface-fusion-treated glass particles provide a uniform wettability on particle surfaces, a binder (64) is uniformly deposited on the surfaces of glass particles (63) when glass powder has been printed, thus reducing the possibility of combustion gas remaining in a dielectric glass layer as bubbles. The finished dielectric glass layer has fewer bubbles (AH), as shown in Fig. 6(d), than that shown in Fig. 6(b).

[統葉有]

THE UNIVERSITY OF CHICAGO

WO 01/43158 A1